optima SDE new AB

CONSTRUCTION STRUCTURE STRUKTUR STRUCTUUR	Tufting 1/10" cut pile COC Tufté 1/10" velours COC Getuftet 1/10" COC-Velours Getuft 1/10" velours COC
PILE MATERIAL COMPOSITION DU VELOURS POLMATERIAL POOLMATERIAAL	100% PA 6 IMPREL®
PRIMARY BACKING SUPPORT TRÄGERMATERIAL TUFTDOEK	Woven PP PP tissé Bändchengewebe PP Geweven PP
SECONDARY BACKING DOSSIER RÜCKEN TAPIJTRUG	Action Back
PILE WEIGHT POIDS DU VELOURS POLEINSATZGEWICHT POOLGEWICHT	Ca. 750 gr/m²
TOTAL WEIGHT POIDS TOTAL GESAMTGEWICHT TOTAAL GEWICHT	Ca. 1.680 gr/m²
PILE HEIGHT EPAISSEUR DU VELOURS POLHÖHE POOLHOOGTE	Ca. 4 mm
TOTAL HEIGHT EPAISSEUR TOTAL GESAMTHÖHE TOTALE DIKTE	Ca. 6 mm
TUFT DENSITY NOMBRES DE POINTS NOPPENZAHL AANTAL PUNTEN	Ca. 256 000/m²
PILE DENSITY DENSITÉ DU VELOURS POLROHDICHTE POOLDICHTHEID	Ca. 0.125 g/cm³
CLASSIFICATION CLASSEMENT KLASSIFIKATION CLASSIFICATIE	EN 1307 32 - LC2
UPEC	U3 P3 E1 C0 Certification CSTB:09/260
CASTOR CHAIR SUITABILITY CHAISE À ROULETTES STUHLROLLENEIGNUNG ROLSTOELGESCHIKTHEID	EN 985 A: intensive use
STAIR SUITABILITY ESCALIERS TREPPENEIGNUNG TRAPPENGESCHIKTHEID	EN 1963 A: intensive use

PERMANENTLY ANTISTATIC ANTISTATIQUE PERMANENT PERMANENT ANTISTATISCH PERMANENT ANTISTATISCH	ISO 6356 < 2 kV
IMPACT NOISE RATING ISOLATION PHONIQUE TRITTSCHALLVERBESSERUNG GELUIDSISOLATIE	ISO 140-8 25 dB ΔLw
SOUND ABSORPTION ABSORPTION PHONIQUE SCHALLABSORPTIONSGRAD GELUIDSABSORPTIE	ISO 354 0.20 αw
THERMAL RESISTANCE RÉSISTANCE THERMIQUE WÄRMEDURCHLASSWIDERSTAND WARMTEDOORLAATWEERSTAND	ISO 8302 0.07 m² K/W
FASTNESS TO LIGHT SOLIDITÉ A LA LUMIÈRE LICHTECHTHEIT LICHTECHTHEID	ISO 105-B02 ≥ 5-6
COLOUR FASTNESS TO WATER SOLIDITÉ À L'EAU WASSERECHTHEIT WATERECHTHEID	EN ISO 105-E01 ≥ 4-5
FIRE RESISTANCE COMPORTEMENT AU FEU BRENNVERHALTEN BRANDGEDRAG	EN 13501-1 Cfl-s1 (if glued)
RUBBING FASTNESS SOLIDITÉ AU FROTTEMENT REIBECHTHEIT WRIJFECHTHEID	EN ISO 105-X12 ≥ 4
NUMBER OF COLOURS NOMBRES DE COULEURS ANZAHL FARBEN AANTAL KLEUREN	16
WIDTH LARGEUR BREITE BREEDTE	EN ISO 3018 ca. 400 cm (16 colours) ca. 500 cm (11 colours)

TÜV NORD Systems – Voluntary Material Test – Suitable for Allergic Persons – Wall to wall carpet of allergen-tested material – 3.2-2384/05

EMISSIONS DANS L'AIR INTÉRIEUR A+ A B C

QB UPEC

REG. NR 80E2C5AE www.pro-dis.info

GUT TESTED – CARPETS TESTED FOR A BETTER LIVING ENVIRONMENT

EN14041 CE

13

Balta Industries - Kanegem-straat 15 - BE 8700 Tielt

DOP: 1011#IE0ACV

Textile Floor Covering EN1307

Notified body 0493

Cfl-s1 DL PCP NA HCHO DS

www.baltamediabank.com

arc edition performance flooring

03/2017 We reserve all rights for technical improvements.

Balta Industries nv - Division ITC - Kanegemstraat 15 - B-8700 Tielt - Belgium - T +32 (0)51 42 44 11 - F +32 (0)51 42 44 85 - info@arcedition.com - www.arcedition.com

optima SDE new AB

▲35 4&5m



▲27 4m

▲16 4&5m

▲64 4&5m

▲43 4m

▲34 4&5m

▲91 4&5m

▲19 4m



▲47 4&5m

▲44 4&5m

▲196 4&5m

▲177 4m

▲71 4&5m

▲73 4m

▲179 4&5m

▲95 4&5m

arc **edition**
performance flooring

Balta Industries nv - Division ITC - Kanegemstraat 15 - B-8700 Tielt - Belgium - T +32 (0)51 42 44 11 - F +32 (0)51 42 44 85 - info@arcedition.com - www.arcedition.com